



## Zen-star 65 Eco PRODUCT CODE – PL 65135



## **TECHNICAL SPECIFICATIONS**

PROPERTIES	TEST METHOD	VALUES FPS UNITS	TEST METHOD	VALUES FPS UNITS
SPECIFIC GRAVITY	DIN 53508	$1.35 \pm 0.05$	ASTM D297	1.35 ±0.05
HARDNESS	DIN 53505	65 ± 5 Sh A	ASTM D2240	65 ± 5 Sh A
TENSILE STRENGTH ( min )	DIN 53504	710 PSI	ASTM D412	60 kg/cm 2
ELONGATION AT BREAK ( min )	DIN 53504	300%	ASTM D412	300%
COMPRESSION SET (70°C/22 hrs/25% compression) (max)	DIN 53517	55%	ASTM D395 METHOD B	55%
TEAR RESISTANCE (Angular) min	DIN 53515	123 Lbs/Inch	ASTM D624	22 Kg/cm
ABRASION RESISTANCE ( max )	DIN 53516	250 mm <sup>3</sup> (10 N)	ASTM D5963	250 mm <sup>3</sup> (10N)
CHANGE IN PROPERTIES AFTER				TM
HEAT AGEING FOR (72 hrs. AT 70 °C )			ASTM D573	
HARDNESS (Pts)		+5 (Max)		+5 (Max)
TENSILE STRENGTH (%)		+10 / -25		+10 / -25
ELONGATION AT BREAK (%)		+10 / -25		+10 / -25
VOLUME SWELL : AT 70°C FOR 72 HRS			ASTM D 471	
IN IRM OIL NO.901		NOT RECOMMENDED		NOT RECOMMENDED
IN IRM OIL NO.902		NOT RECOMMENDED		NOT RECOMMENDED
IN IRM OIL NO.903		NOT RECOMMENDED		NOT RECOMMENDED
CHEMICAL RESISTANCE				
OZONE		NOT RECOMMENDED	149	NOT RECOMMENDED
DILUTE ACIDS AND BASES		NOT RECOMMENDED		NOT RECOMMENDED
CONCENTRATED ACIDS AND BASES		NOT RECOMMENDED		NOT RECOMMENDED
OILS		NOT RECOMMENDED		NOT RECOMMENDED
SOLVENTS		NOT RECOMMENDED		NOT RECOMMENDED
TEMPERATURE RANGE		-30° to + 70° C		-30 ° to + 70° C
COLOR		BLACK		BLACK
DESIGN		MEDIUM, MAX, I DESIGN	MINI DIAMOND	

Note: All pictures shown are for illustration purpose only. Actual product may vary due to product enhancement.\*





















