


ABRA SUPER 40

PRODUCT CODE – ABRA SUPER 40



TECHNICAL SPECIFICATIONS

PROPERTIES	TEST METHOD	VALUES FPS UNITS	TEST METHOD	VALUES FPS UNITS
SPECIFIC GRAVITY	DIN 53508	0.98 ±0.05	ASTM D297	0.98 ±0.05
HARDNESS	DIN 53505	38 ± 5 Sh A	ASTM D2240	38 ± 5 Sh A
TENSILE STRENGTH (min)	DIN 53504	3627 PSI	ASTM D412	255 kg/cm 2
ELONGATION AT BREAK (min)	DIN 53504	810%	ASTM D412	810 %
ABRASION RESISTANCE (max)	DIN 53516	90 mm ³ (5 N)	ASTM D5963	90 mm ³ (5 N)
COMPRESSION SET (70°C/24 hrs/25% compression) (max)	DIN 53517	30 %	ASTM D395 METHOD B	20 %
TEAR RESISTANCE (Angular) min	DIN 53515	250 Lbs/Inch	ASTM D624	44 Kg/cm
CHANGE IN PROPERTIES AFTER				
HEAT AGEING FOR (72 hrs. AT 70 °C)			ASTM D573	
--- HARDNESS (Pts)		+ 3 (Max)		+ 3 (Max)
--- TENSILE STRENGTH (%)		+10/-25		+10 /- 25
--- ELONGATION AT BREAK (%)		+10/-25		+10 /- 25
VOLUME SWELL : AT 70°C FOR 72 HRS			ASTM D 471	
IN IRM OIL NO.901		NOT RECOMMENDED		NOT RECOMMENDED
IN IRM OIL NO.902		NOT RECOMMENDED		NOT RECOMMENDED
IN IRM OIL NO.903		NOT RECOMMENDED		NOT RECOMMENDED
CHEMICAL RESISTANCE				
--- OZONE		NOT RECOMMENDED	ASTM D 1149	NOT RECOMMENDED
--- DILUTE ACIDS AND BASES		GOOD		GOOD
--- CONCENTRATED ACIDS AND BASES		NOT RECOMMENDED		NOT RECOMMENDED
--- OILS		NOT RECOMMENDED		NOT RECOMMENDED
--- SOLVENTS		NOT RECOMMENDED		NOT RECOMMENDED
TEMPERATURE RANGE		-40° to + 75° C		-30 ° to + 75° C
COLOR		RED		RED

Note: All pictures shown are for illustration purpose only. Actual product may vary due to product enhancement.*

