


ABRA FRAS ECO

PRODUCT CODE – NR 70140



TECHNICAL SPECIFICATIONS

PROPERTIES	TEST METHOD	VALUES FPS UNITS	TEST METHOD	VALUES FPS UNITS
SPECIFIC GRAVITY	DIN 53508	1.10 ± 0.05	ASTM D297	1.10 ± 0.05
HARDNESS	DIN 53505	70 ± 5 Sh A	ASTM D2240	70 ± 5 Sh A
TENSILE STRENGTH (min)	DIN 53504	2133 PSI	ASTM D412	150 kg/cm 2
ELONGATION AT BREAK (min)	DIN 53504	400 %	ASTM D412	400 %
ABRASION RESISTANCE (max)	DIN 53516	200 mm ³	ASTM D5963	200 mm ³
COMPRESSION SET (70°C/24 hrs/25% compression) (max)	DIN 53517	20 %	ASTM D395 METHOD B	20 %
TEAR RESISTANCE (Angular) min	DIN 53515	252 Lbs/Inch	ASTM D624	45 Kg/cm
CHANGE IN PROPERTIES AFTER				
HEAT AGEING FOR (72 hrs. AT 70 °C)			ASTM D573	
--- HARDNESS (Pts)		+ 5 (Max)		+ 5 (Max)
--- TENSILE STRENGTH (%)		+10 /-25		+10 /-25
--- ELONGATION AT BREAK (%)		+10 /-25		+10 /-25
VOLUME SWELL : AT 70°C FOR 72 HRS	ASTM D 471			
IRM OIL NO.901		NOT RECOMENDED		NOT RECOMENDED
IRM OIL NO.902		NOT RECOMENDED		NOT RECOMENDED
IRM OIL NO.903		NOT RECOMENDED		NOT RECOMENDED
CHEMICAL RESISTANCE				
--- OZONE		FAIR	ASTM D 1149	FAIR
--- DILUTE ACIDS AND BASES		NOT RECOMENDED		NOT RECOMENDED
--- CONCENTRATED ACIDS AND BASES		NOT RECOMENDED		NOT RECOMENDED
--- OILS		NOT RECOMENDED		NOT RECOMENDED
--- SOLVENTS		NOT RECOMENDED		NOT RECOMENDED
TEMPERATURE RANGE		-30° to + 70° C		-30 ° to + 70° C
COLOR		BLACK		BLACK

Note: All pictures shown are for illustration purpose only. Actual product may vary due to product enhancement.*

