

## Abra-Super 40 PRODUCT CODE – Abra-Super 40



## **TECHNICAL SPECIFICATIONS**

PROPERTIES	TEST METHOD	VALUES FPS UNITS	TEST METHOD	VALUES
				FPS UNITS
SPECIFIC GRAVITY	-	$0.98 \pm 0.05$	ASTM D297	$0.98 \pm 0.05$
HARDNESS	ISO 48-4	38 ± 5 Sh A	ASTM D2240	38 ± 5 Sh A
TENSILE STRENGTH ( min )	ISO 37	3627 PSI	ASTM D412	255 kg/cm 2
ELONGATION AT BREAK ( min )	ISO 37	900 %	ASTM D412	900 %
TEAR RESISTANCE (Angular) min	ISO 34-1	250 Lbs/Inch	ASTM D624	44 Kg/cm
ABRASION RESISTANCE ( max )	ISO 4649	90 mm3 (5 N)	ASTM D5963	90 mm3 (5 N)
COMPRESSION SET (70°C/24 hrs/25% compression) (max)	ISO 815-1	30 %	ASTM D395 METHOD B	30 %
CHANGE IN PROPERTIES AFTER				
HEAT AGEING FOR (72 hrs. AT 70 °C)			ASTM D573	
HARDNESS (Pts)		+ 3 (Max)		+ 3 (Max)
TENSILE STRENGTH (%)		+ 10 / - 25		+ 10 / - 25
ELONGATION AT BREAK (%)		+ 10 / - 25		+ 10 / - 25
VOLUME SWELL : AT 70°C FOR 72 HRS			ASTM D 471	
IN IRM OIL NO.901		NOT RECOMMENDED		N <mark>OT</mark> RECOMMENDED
IN IRM OIL NO.902		NOT RECOMMENDED		NOT RECOMMENDED
IN IRM OIL NO.903		NOT RECOMMENDED		NOT RECOMMENDED
CHEMICAL RESISTANCE				
OZONE		NOT RECOMMENDED	ASTM D 1149	NOT RECOMMENDED
DILUTE ACIDS AND BASES		GOOD		GOOD
CONCENTRATED ACIDS AND BASES		NOT RECOMMENDED		NOT RECOMMENDED
OILS		NOT RECOMMENDED		NOT RECOMMENDED
SOLVENTS		NOT RECOMMENDED		NOT RECOMMENDED
TEMPERATURE RANGE		-40° to + 75° C		-40 ° to + 75° C
COLOR		RED		RED

Note: All pictures shown are for illustration purpose only. Actual product may vary due to product enhancement.\*























