

ABRA SUPER 60 OZ

PRODUCT CODE – Abra-Super OZ 60



TECHNICAL SPECIFICATIONS

PROPERTIES	TEST METHOD	VALUES FPS UNITS	TEST METHOD	VALUES FPS UNITS
SPECIFIC GRAVITY	-	1.05 ±0.05	ASTM D297	1.05 ±0.05
HARDNESS	ISO 48-4	60 ± 5 Sh A	ASTM D2240	60 ± 5 Sh A
TENSILE STRENGTH (min)	ISO 37	3129 PSI	ASTM D412	220 kg/cm 2
ELONGATION AT BREAK (min)	ISO 37	750 %	ASTM D412	750 %
ABRASION RESISTANCE (max)	ISO 4649	140 mm ³ (10 N)	ASTM D5963	140 mm ³ (10 N)
COMPRESSION SET (70°C/24 hrs/25% compression) (max)	ISO 815-1	40 %	ASTM D395 METHOD B	40 %
TEAR RESISTANCE (Angular) min	ISO 34-1	280 Lbs/Inch	ASTM D624	50 Kg/cm
CHANGE IN PROPERTIES AFTER				
HEAT AGEING FOR (72 hrs. AT 70 °C)			ASTM D573	
--- HARDNESS (Pts)		+ 5 (Max)		+ 5 (Max)
--- TENSILE STRENGTH (%)		+10/-25		+10 /- 25
--- ELONGATION AT BREAK (%)		+10/-25		+10 /- 25
VOLUME SWELL : AT 70°C FOR 72 HRS			ASTM D 471	
IN IRM OIL NO.901		NOT RECOMMENDED		NOT RECOMMENDED
IN IRM OIL NO.902		NOT RECOMMENDED		NOT RECOMMENDED
IN IRM OIL NO.903		NOT RECOMMENDED		NOT RECOMMENDED
CHEMICAL RESISTANCE				
--- OZONE		NO CRACK	ASTM D 1149	NO CRACK
--- DILUTE ACIDS AND BASES		GOOD		GOOD
--- CONCENTRATED ACIDS AND BASES		NOT RECOMMENDED		NOT RECOMMENDED
--- OILS		NOT RECOMMENDED		NOT RECOMMENDED
--- SOLVENTS		NOT RECOMMENDED		NOT RECOMMENDED
TEMPERATURE RANGE		-40° to + 75° C		-30 ° to + 75° C
COLOR		BLACK / GREEN		BLACK / GREEN

Note: All pictures shown are for illustration purpose only. Actual product may vary due to product enhancement.*

