


# ABRA SUPER 60

## PRODUCT CODE – ABRA SUPER 60



### TECHNICAL SPECIFICATIONS

PROPERTIES	TEST METHOD	VALUES FPS UNITS	TEST METHOD	VALUES FPS UNITS
SPECIFIC GRAVITY	-	1.10 ±0.05	ASTM D297	1.10 ±0.05
HARDNESS	ISO 48-4	60 ± 5 Sh A	ASTM D2240	60 ± 5 Sh A
TENSILE STRENGTH ( min )	ISO 37	3840 PSI	ASTM D412	270 kg/cm 2
ELONGATION AT BREAK ( min )	ISO 37	800 %	ASTM D412	800 %
ABRASION RESISTANCE ( max )	ISO 4649	100 mm <sup>3</sup> (5 N)	ASTM D5963	100 mm <sup>3</sup> (5 N)
COMPRESSION SET (70°C/24 hrs/25% compression) (max)	ISO 815-1	30 %	ASTM D395 METHOD B	20 %
TEAR RESISTANCE ( Angular ) min	ISO 34-1	336 Lbs/Inch	ASTM D624	60 Kg/cm
CHANGE IN PROPERTIES AFTER				
HEAT AGEING FOR ( 72 hrs. AT 70 °C )			ASTM D573	
--- HARDNESS (Pts)		+ 5 (Max)		+ 5 (Max )
--- TENSILE STRENGTH (%)		+10/-15		+10 /- 15
--- ELONGATION AT BREAK (%)		+10/-25		+10 /- 25
VOLUME SWELL : AT 70°C FOR 72 HRS			ASTM D 471	
IN IRM OIL NO.901		NOT RECOMMENDED		NOT RECOMMENDED
IN IRM OIL NO.902		NOT RECOMMENDED		NOT RECOMMENDED
IN IRM OIL NO.903		NOT RECOMMENDED		NOT RECOMMENDED
CHEMICAL RESISTANCE				
--- OZONE		NOT RECOMMENDED	ASTM D 1149	NOT RECOMMENDED
--- DILUTE ACIDS AND BASES		GOOD		GOOD
--- CONCENTRATED ACIDS AND BASES		NOT RECOMMENDED		NOT RECOMMENDED
--- OILS		NOT RECOMMENDED		NOT RECOMMENDED
--- SOLVENTS		NOT RECOMMENDED		NOT RECOMMENDED
TEMPERATURE RANGE		-30° to + 70° C		-30 ° to + 70° C
COLOR		RED/BLACK		RED/BLACK

Note: All pictures shown are for illustration purpose only. Actual product may vary due to product enhancement.\*

