


# SILICON 60120 FG

## PRODUCT CODE – SI 60120 FG



### TECHNICAL SPECIFICATIONS

PROPERTIES	TEST METHOD	VALUES	TEST METHOD	VALUES
		FPS UNITS		FPS UNITS
SPECIFIC GRAVITY	DIN 53508	1.20 ± 0.05	ASTM D297	1.20 ± 0.05
HARDNESS	DIN 53505	60 ± 5 Sh A	ASTM D2240	60 ± 5 Sh A
TENSILE STRENGTH ( min )	DIN 53504	853 PSI	ASTM D412	60 kg/cm 2
ELONGATION AT BREAK ( min )	DIN 53504	250 %	ASTM D412	250 %
TEAR RESISTANCE ( Angular ) min	DIN 53515	112 Lbs/Inch	ASTM D624	20 Kg/cm
COMPRESSION SET (70°C/24 hrs/25% compression) (max)	DIN 53517	45 %	ASTM D395 METHOD B	45 %
CHANGE IN PROPERTIES AFTER				
HEAT AGEING FOR ( 72 hrs. AT 70 °C )			ASTM D573	
--- HARDNESS (Pts)		+3 (max)		+3 (max)
--- TENSILE STRENGTH (%)		+5 / 5		+5 / -5
--- ELONGATION AT BREAK (%)		+5 / -5		+5 / - 5
VOLUME SWELL : AT 70°C FOR 72 HRS			ASTM D 471	
IN IRM OIL NO.901		NOT RECOMMENDED		NOT RECOMMENDED
IN IRM OIL NO.902		NOT RECOMMENDED		NOT RECOMMENDED
IN IRM OIL NO.903		NOT RECOMMENDED		NOT RECOMMENDED
CHEMICAL RESISTANCE				
--- OZONE		EXCELLENT		EXCELLENT
--- DILUTE ACIDS AND BASES		EXCELLENT		EXCELLENT
--- CONCENTRATED ACIDS AND BASES		EXCELLENT		EXCELLENT
--- OILS		NOT RECOMMENDED		NOT RECOMMENDED
--- SOLVENTS		NOT RECOMMENDED		NOT RECOMMENDED
TEMPERATURE RANGE		-90° to + 220° C		-90° to + 220° C
COLOR		WHITE / BRICK RED / BLUE		WHITE / BRICK RED / BLUE

Note: All pictures shown are for illustration purpose only. Actual product may vary due to product enhancement.\*